

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

**TEST CERTIFICATE**

<b>CLIENT:</b>	Agua Fabrics Ltd Hyde House The Hyde London NW9 6LH -	<b>Certificate Number:</b>	<b>UK1800046 -6</b>
		<b>Date Received:</b>	23/01/2018
		<b>Date Issued:</b>	24/01/2018
		<b>Issue Number:</b>	1
<b>Contact:</b>	Suzanne Ralton	Changes from previous issue (if applicable)	
<b>Tel:</b>	020820500050	_____	
<b>Email:</b>	suzanne@aguafabrics.com		

<b><u>SAMPLE IDENTIFICATION</u></b>	
Sample Name / Reference:	Parody
Order / Batch No:	Jan 2018 Vinyl FR Testing
Customer:	Agua Fabrics Ltd
Fabric Composition:	PVC
Colour:	-
Quality:	Parody
Width:	140cm

<b><u>SPECIFICATION</u></b>	
BS7176:2007 + A1:2011 - Medium Hazard	
<b><u>TEST METHOD</u></b>	
Flammability:	BS EN 1021-1:2006 Part 1: Ignition source smouldering cigarette BS EN 1021-2:2006 Part 2: Ignition source match flame equivalent BS 5852:2006 Crib Ignition source 5
Pre-treatment:	None-Requested

<b><u>Conclusion</u></b>	
The composite tested:	<b>Complies</b> with the flammability requirements of: BS 7176:2007 + A1:2011 Medium hazard, taking into account uncertainty of measurement.

Please note that copies of this original certificate are not valid

<b><u>Comments and Observations:</u></b> -Cigarettes did not burn to completion
--

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

**TEST CERTIFICATE****Test Results:-****BS7176:2007 + A1:2001 - Medium Hazard - Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites**

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

Sample Code	UK1800046 -6					
Sample / Name Reference	Parody					
Client	Agua Fabrics Ltd					
Date of test	24/01/2018					
Pre-Treatment	None-Requested - at ambient temperature					
Filling Type	Carpenter/RX36110 unmodified polyurethane foam of density 33Kg/m3/Type B, 130					
Size of test rig	Small: Back - 450 x 300 ± 2mm + Seat - 450 x 150 ± 2mm					
Test Conditions	Period h	Temperature °C	Relative humidity %	Air Flow m/s	Volume m <sup>3</sup>	
Conditioning of test specimens	≥16	23±2	50±5	-	-	
Testing conditions	-	10-30	15-80	0.02-0.2	>20	
Testing Source	BS EN 1021-1:2006 Smouldering Cigarette Source					
Testing time limit	60 minutes after placement of smouldering cigarette.					
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	LHS	NI	2.52	0	2.58	-
2	M	NI	2.15	0	2.31	-
3	RHS	NI	3.04	0	3.14	-
Testing Source	BS EN 1021-2:2006 Match flame ignition source					
Testing time limit	2 minutes after removal of burner tube (120 seconds)					
Test No.	Position	Ignition/N on Ignition	Duration of: (sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	LHS	NI	15	15	21	-
2	M	NI	15	15	22	-
3	RHS	NI	15	15	22	-
<b>RESULT:</b>	<b>SMOULDERING CIGARETTE SOURCE</b>				<b>PASS</b>	
	<b>MATCH FLAME IGNITION SOURCE</b>				<b>PASS</b>	
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side						

Please note that copies of this original certificate are not valid

**Issue Number: 1**

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

# TEST CERTIFICATE


**Test Results:-****BS7176:2007 + A1:2001 - Medium Hazard - Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites***"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."*


Sample Code	UK1800046 -6									
Sample Reference	Parody									
Client	Agua Fabrics Ltd									
Date of test	24/01/2018									
Pre-Treatment	None-Requested -									
Filling Type	Carpenter/RX36110 unmodified polyurethane foam of density 33Kg/m3/Type B, 130									
Size of test rig	Large: Back - 450 x 450 ± 2mm + Seat - 450 x 300 ± 2mm									
Test Conditions	Period h	Temperature °C	Relative humidity %	Air Flow m/s	Volume m <sup>3</sup>					
Conditioning of test specimens	≥16	23±2	50±5	-	-					
Testing conditions	-	10-30	15-80	0.02-0.2	>20					
Testing Source	BS 5852:2006 Crib Ignition source 5									
Testing time limit	10 minutes after ignition of crib. Observed for 60 minutes in total.									
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)		Extent of Damage to component: mm					
			Flames	Smoke	Horizontal			Vertical		
					Width	Length	Depth	Width	Depth	
1	M	NI	4.17	6.38	87	65	26	88	27	
2	M	NI	4.33	6.22	80	67	27	82	34	
<b>RESULT:</b>		<b>CRIB IGNITION SOURCE 5</b>						<b>PASS</b>		

KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side

Test No.	Time for: (sec)		
	Ignition of test pieces	Cover Splitting	Extinction
1	-	-	-
2	-	-	-

On behalf of Lancashire Testing Services :

Tony Alcock,  
Laboratory Technician:
  
 John Marsh,  
Laboratory Technician:

  
 Peter Collings,  
Operations Manager:

Please note that copies of this original certificate are not valid

**Issue Number: 1**

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality